

### CERATUFF-90 SPECIFICATIONS

S.No	Properties	Value
1.	Composition	>92% Alumina
2.	Average crystal size	4-6 micron
3.	Specific gravity	> 3.6
4.	Fusion temperature	1500deg C
5.	Maximum use temperature	1000 deg C
6.	Compressive strength (20 Degree Centigrade)	>3200kg/cm2
7.	Flexural strength (20 Degree Centigrade)	>2200kg/cm2
8.	Hardness (On Moh scale Hv 10)	9
9.	Porosity	nil
10.	Modulus of Rupture	1200kg/cm2
11.	Coefficient of thermal expansion (20-1000 Degree Centigrade)	7.2 x10 <sup>-6</sup> per deg C
12.	Density	3.6 gm/cc
13.	Corrosion Resistant (mg/cm <sup>2</sup> /day) with 95% H2So4 at 20 degree Centigrade	0.03mg/cm2/day
14.	Abrasion Test Loss	0.03gm. max
15.	Jet Erosion Test 45 deg	0.02max
16.	90 deg	0.04max

All the value above are average value and for reference only.

HOFMANN ENGG. & MKTG. P. LTD.  
WEAR RESISTANT TECHNOLOGY DIVISION  
307, SHUBHAM COMPLEX,  
VASTRAPUR, AHMADABAD-380054  
GUJARAT, INDIA.  
TEL: +91 79 26853867/40053867  
FAX: +91 79 26850175  
EMAIL: info@hofmannindia.com  
Web: www.Hofmannindia.com